# MARC 1 A





MARC 1 A

Manual Pad Welding System (Air cooled) for pad welding with rotating arc

#### Technical Data

| Welding range       | M6 to M10 (pad)*  |
|---------------------|---|
| Welding material    | Stainless steel, steel (on request)   |
| Welding rate        | 4 pieces/min**  |
| Wall thickness      | Up to 2.5 mm***   |
| Welding current     | 1,000 A (max.)  |
| Welding time        | 5 to 1,000 msec (stepless)  |
| Primary power       | 400 V (alternative input voltages available), 32 A, 3 phases, 50/60 Hz, 35 AT (IT 1002)   |
| Power source        | Inverter  |
| Field former unit   | Not controlled  |
| Protection class    | IP 23   |
| Dimension L x W x H | 660 x 280 x 340 mm (IT 1002) without handle   |
| Weight              | 29 kg (IT 1002)   |
|                     | <ul> <li>* due to a possible replacement of the manual welding gun, the unit is also suitable<br/>for manual stud welding</li> <li>** depending on pad diameter and material</li> <li>*** higher wall thickness on request</li> </ul> |
| Order No.           | MARC1.A   |
|                     | Consists of:<br>Stud welding unit IT 1002<br>Ground cable<br>Welding gun AM 30 A<br>Field former FA1 (equipped for one standard dimension)<br>Shielding gas tripod MARC1.A/MARC1.W  |
| General Information |   |

#### General Information

Application

- Welding of threaded pads and welding nuts
- Welding on punched and unpunched sheets
- Especially suited for shop and installation applications

Options

Gas control module 2-channel



## Advantages

### Description

- Low energy consumption
- Even and minimal heat input (low distortion)
- Very short welding time (≤ 1 second) and consequently short cycle time in production
- No welding additives required
- Minimum upset force
- Small and even welding seam
- Only one-sided accessibility to the work piece required
- Low investment costs for machine technique
- Extremely clean process (minimum development of airborne particles)
- No reworking of work piece or welding element (thread)

Issue 12/08

(Technical data may change)